



Name	Item Number	Type	Curable	Base /Additive	Maximum PC Loading	User Levels	Effect
SPEC Base	10-1002	Transparent	yes	base	20%	up to 20%	softening viscosity and hand
Soft Hand Base	10-0111	Transparent	yes	base	20%	up to 20%	softening viscosity and hand
Opac Base	12-1002	Filled	yes	Base	28%		For mixing colors from PC
G & S Base	10-1020	Clear	yes	base	15%	up to 50%	stretch for lycar and gloss coatings
Hi-Den Base	51-1026	Clear	yes	n/a			for clear gel top coating
Puff Base	10-9950	non pigment	yes	base	25%		for mixing colors puff from PC
Suede Base	10-9967	non pigment	yes	base	25%		for mixing suede color puff from pc
Curable Reducer	10-9906	Clear	yes	additive	15%	up to 15%	for reducing viscosity
FR Additive	10-9971		no	additive	n/a	10%	for making ink flame retardent
Hot split Additive	10-9908		no	additive	n/a	10%	for making hot split ink
Suede Additive	10-9907		no	additive	n/a	10%	for making suede puff ink
Puff Additive	10-9903		no	additive	n/a	10 to 15%	for making puff inks
Dull Additive	10-9907		no	additive		up to 5%	for dulling the gloss of inks
Nylon Bonding Agent	YNB-W100		no	additive	n/a	10 to 15%	for adhesion to nylon fabrics
Long Life Bonding	YAL-W200		no	additive	n/a	10 to 15%	for adhesion to nylon fabrics
First down clear	10-1033	Transparent	yes	base	n/a	UP TO 30%	For improving gelling, toughness and bleed resistance
Thickener	56-1002		no	additive	n/a	up to 2%	A powder to thicken ink
Hot Split Base	41-1004	Filled	yes	base	20%	n/a	for mixing Hot Split color from PC
G & S Base	10-1020	Clear	yes	base	20% flake		for mixing Glitter Flake in
FR Base	10-1142	Filled	yes	base	20%		For mixing FR Color from PC

4237 Raleigh Street Charlotte NC 28213 704-535-4657